

GOLDEN GATE

Colours | Farben | Couleurs

005



GG005-27152



GG005-31129



GG005-31242



GG005-31491

CARUS®

Balsan S.A.S.
B.P. 50 - 2, Corbilly
F-36330 ARTHON

Tél. +33 254 29 16 00
Fax. +33 254 36 79 08

carus@carusflooring.com
www.carusflooring.com

GOLDEN GATE

Technical specifications | Technische Daten | Spécifications techniques

Manufacturing technique Herstellungstechnik Technique de fabrication	1/10 Cut Pile Velours à Saxony imprimé	Total weight Gesamtgewicht Poids total	ISO 8543	2350 g/m ²
Pile composition Material der Nutzschrift Composition du velours	100% Nylon 100% Polyamid 100% Polyamide	Number of tufts Noppenzahl Nombre de points	ISO 1763	189 000/m ²
Secondary backing Rückenausstattung Dossier	Fusion Back	Fastness to rubbing (dry) Reibechtheit (trocken) Solidité au frottement (sec)	ISO 105 X12	4-5
Width Breite Largeur	400 cm	Fastness to rubbing (wet) Reibechtheit (nass) Solidité au frottement (humide)	ISO 105 X12	4-5
Roll length Rollenlänge Longeur du rouleau	± 25 ml	Water fastness Wasserechtheit Solidité à l'eau	ISO 105 E01	4-5
Pile height Polhöhe Hauteur du velours	ISO 1766 6,5 mm	Fastness to light Lichtechtheit Solidité à la lumière	ISO 105 B2	5-6/8
Pile weight Polgewicht Poids du velours	1300 g/m ²	Thermal resistance Wärmedurchlasswiderstand Résistance thermique	ISO 8302	<0,15 m ² C°/W
Total height Gesamthöhe Hauteur totale	ISO 1765 10 mm	Impact sound insulation Trittschalldämmung Réduction de la transmission du bruit de choc	ISO 140 - 8	25 dB
DOP Nr / DOP n°	1009#129686			



CARUS®

Balsan S.A.S.
B.P. 50 - 2, Corbilly
F-36330 ARTHON

Tél. +33 254 29 16 00
Fax. +33 254 36 79 08

carus@carusflooring.com
www.carusflooring.com